



INTERNATIONAL PUBLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09J 9/02	A1	(11) International Publication Number: WO 99/24520 (43) International Publication Date: 20 May 1999 (20.05.99)
(21) International Application Number: PCT/US98/22329 (22) International Filing Date: 21 October 1998 (21.10.98) (30) Priority Data: 08/964,139 6 November 1997 (06.11.97) US (63) Related by Continuation (CON) or Continuation-in-Part (CIP) to Earlier Application US 08/964,139 (CON) Filed on 6 November 1997 (06.11.97) (71) Applicant (for all designated States except US): LAMBDA TECHNOLOGIES, INC. [US/US]; Suite 900, 960 Aviation Parkway, Morrisville, NC 27560 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): WEI, Jianghua [CN/US]; 4100-186 Deep Hollow Drive, Raleigh, NC 27612 (US). FATHI, Zakaryae [MA/US]; 101 H Stephanie Drive, Cary, NC 27511 (US). (74) Agents: SAJOVEC, F., Michael et al.; Myers, Bigel, Sibley, & Sajovec, P.A., P.O. Box 37428, Raleigh, NC 27627 (US).		(81) Designated States: AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), EE, EE (Utility model), ES, FI, FI (Utility model), GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, ML, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: MICROWAVE CURABLE ADHESIVE (57) Abstract The present invention provides a microwave curable adhesive comprising a polymer composition (e.g., a thermoplastic or thermoset polymer) and first and second microwave susceptible components. The first and second microwave susceptible components have a respective preselected size, preselected shape or preselected conductivity or combination thereof. These properties are selected to provide a multi-modal distribution of first and second microwave susceptible components and to increase microwave adsorption within said polymer composition.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

MICROWAVE CURABLE ADHESIVE
Field and Background of the Invention

The present invention relates to microwave curable adhesives, and compositions and methods for improving the curing thereof.

Conventionally, thermoplastic and thermoset adhesives are cured using radiant
5 heat or chemical reactions through the use of a catalyst or initiator. In an effort to reduce the cure time often required by these techniques, it has been suggested to use ultrasonic or electromagnetic techniques. See, for example, U.S. Patent Nos. 3,620,876 to Guglielmo, Sr. et al; 4,219,361 to Sutton et al.; and 5,248,864 to Kodokian. Ultrasonic bonding utilizes acoustical properties of the material to be
10 bonded. Electromagnetic bonding is accomplished by one of three methods: (a) magnetic energy induction; (b) dielectric energy generation; or (c) microwave generation. There is a particular interest in the use of microwave generation in that it permits articles to be bonded by rapidly curing the adhesive.

Heat is generated in materials irradiated with microwaves in accordance with
15 either orientation polarization or equivalent resistance heating. The operative mechanism is dependent upon the operating frequency. Orientation polarization is perhaps the most important mechanism of polarization in the microwave frequency range. Equivalent resistance heating results from the flow of conductive current in the substance. The current is related to electronic conduction and ionic conduction in a
20 material. Equivalent resistance heating is more significant at lower frequencies.

Also known as dipolar polarization, orientation polarization involves the perturbation of the random motion of ionic or molecular dipoles to produce a net dipolar orientation under the direction of an applied electric field. Orientation polarization depends on the internal structure of the molecules and on the molecular
25 arrangement or the structure of the dielectric substance, i.e., the adhesive or substrate.

Thus, each material exhibits a specific dielectric behavior (losses) which is dependent upon the range of temperatures and frequencies used during processing. Dielectric loss measurements of a given material over the range of temperatures and frequencies of interest provide the information necessary to select frequencies and to select those frequencies which optimize heating of that material. For most polymeric materials, the orientation polarization loss peak (maximum loss) shifts to higher frequencies as the temperature of the material is increased.

Many adhesives, however, are not susceptible to microwave curing, or if the adhesives are, curing is slow or difficult to control or both. Thus it has been proposed in, for example, U.S. Patent No. 4,626,642 to Wang et al., to blend electrically conductive fibers into a thermoset adhesive to accelerate cure rates. U.S. Patent No. 4,906,497 to Hellmann et al. proposes the use of electrically conductive materials (e.g., carbon fibers) to accelerate the heating-up rate by microwaves.

In addition, microwaves, particularly single frequency microwaves, are not always uniformly distributed throughout the microwave oven. Differential heating can result in heating only specific portions of the adhesive resulting in uneven curing.

An alternative to single frequency microwaves and this problem of differential heating is to use variable frequency microwaves as is suggested in U.S. Patent No. 5,321,222 to Bible et al. The use of variable frequency microwaves, however, does not typically overcome susceptibility problems.

Thus there remains a need to provide adhesives which are susceptible to curing using various microwave techniques particularly using variable frequency microwaves.

Summary of the Invention

To this end, the present invention provides a microwave curable adhesive comprising a polymer composition (e.g., a thermoplastic or thermoset polymer) and first and second microwave susceptible components. The first and second microwave susceptible components have a respective preselected size, preselected shape or preselected conductivity or combination thereof. These properties are selected to

provide a multi-modal distribution of first and second microwave susceptible components and to increase microwave adsorption within said polymer compositions particularly when cured using variable frequency microwaves.

5 In an alternative embodiment, the microwave curable adhesive comprises a polymer composition and a network of interconnected first and second conductive fibers dispersed within said polymer composition such that said adhesive has a volumetric fraction of first and second conductive fibers of between 0.01% and 2% and a weight fraction of first and second conductive fibers of between 1% and 20%.

10

Brief Description of the Drawings

Figure 1 shows a heating curve according to Example 1.

Figure 2 shows a heating curve according to Example 2.

Detailed Description of the Invention

15

As discussed above, the present invention provides a microwave curable adhesive comprising a polymer composition and microwave susceptible components. The adhesive is susceptible to uniform curing particularly using variable frequency microwaves. Moreover by using variable frequency microwaves and the microwave susceptible components of the present invention, arcing of the microwaves is avoided.

20

The polymer composition is either a thermoplastic or thermoset polymer. Suitable thermoplastic polymers include polyolefins, vinyl polymers, polycarbonates, polyamides, polystyrenes, polyetherimides, polyarylene sulfones, polyphenylene sulfides, polyphenylene oxides, polyethersulfones, polyetherether ketones and blends and copolymers thereof. Suitable thermoset polymers include epoxies, phenol

25

formaldehydes, urea-formaldehydes, melamine formaldehydes, polyesters, polyurethanes, cyanate esters, polybutadienes, alkyals, polyimides, amino resins and silicones and blends and copolymers thereof. Specific preferred polymers include: duPont Elvax, an ethylene/vinyl acetate/acid terpolymer; Henkel Q5355s, a carbon-doped polypropylene; HB Fuller HL 6444; Bemis C5251, a carbon-filled polyester; 30 Bemis 5251, an unfilled polyester; and Bemis 6218, a polyolefin. These adhesives

may contain any of the commonly-employed additives, such as but not limited to, fillers, colorants, curing agents, pigments, and thickening agents.

In an alternative embodiment, the adhesive may be one used to bond materials having deformation temperatures lower than the activation temperature of the adhesive, such as described in U.S. Patent Application entitled "Methods and Apparatus for Bonding Deformable Materials Having Low Deformation Temperatures" filed 6 November 1997, the disclosure of which is incorporated herein by reference in its entirety. Such an adhesive is useful in forming laminates suitable for many purposes such as bonding the soles of footwear, providing durable padding comprising a shock-absorbing padding material layer bonded to at least one wear resistant layer, and the like.

In combination with the thermoplastic or thermoset polymer is a first microwave susceptible component and a second microwave susceptible component. Various properties of these first and second microwave susceptible components are preselected to provide a multi-modal distribution to increase microwave absorption of the variable frequency microwaves particularly within the thermoplastic or thermoset polymer. The multi-modal distribution also allows the heating rate to be increased. Moreover, the overall heating efficiency of the adhesive can be increased without increasing the weight percent loading of adhesive. This results in the viscosity of the adhesive being substantially low so that the adhesive can be easily sprayed onto a substrate. Most of the prior art methods and adhesives have levels of a single microwave susceptible component that prevent the adhesive from being sprayed. Moreover, such microwave susceptible components can cause arcing when conventional single frequency microwaves are used.

In operation, when the microwave susceptible components, e.g., fibers of different length, diameter and/or conductivity are exposed to microwaves, an electric current is generated within the fibers which generates heat inside the fibers. The heat generation is directly proportional to the square of the current generated within the fiber and the electrical resistance of the fiber. The lower the resistivity, the higher the current density. When the applied electric field is sufficiently high, the charge buildup between different fibers will be so high that it surpasses the existing dielectric

resistance imposed by the nonconducting material. The smaller the gap between fibers, the lesser the charge buildup is necessary to cause heat. In order to take the advantage of this heating mechanism, a formation of an interconnecting "semi-conductive path" is required. The "semi-conductive" phenomenon refers to a condition that the microwave susceptible component itself is not conductive but the gaps between the individual microwave susceptible components are sufficiently small for electric breakdown to occur when the applied field is sufficiently high. In other words, the filling factor of the fiber is very important for heat enhancement. The higher the filling factor, the easier for fibers to form an interconnecting network. The amount of microwave susceptible components required to form this network depends on fiber size, distribution, and conductivity. The higher the conductivity, the lesser amount of the components is required to observe this heating mechanism because the charge buildup is more significant. Also, it is desirable to have fibers of different sizes to enhance the heating rate and heating uniformity.

As stated above, the properties of the first and second microwave susceptible components that are preselected are preferably shape, size, or conductivity or combination thereof. For example, the first microwave susceptible component preferably is a fiber having a diameter of about 0.01 to 0.1 μm , a length of about 10 to 300 μm and a conductivity of about 10^{-2} to 10^{-7} Ω/cm . The second microwave susceptible component can be a particle or a fiber. If the second microwave susceptible component is a particle, preferably it has a particle size of about 1 to 40 μm and a conductivity of about 10^{-2} to 10^{-7} Ω/cm .

If the second microwave susceptible component is a fiber then it is preferred that the components be a network of interconnected fibers for the reasons stated above. Moreover, the fibers should be of substantially different sizes. For example, the first microwave susceptible component can have a diameter of about 0.07 to 0.1 μm , a length of about 10 to 300 μm and conductivity of about 10^{-2} to 10^{-7} , the second microwave susceptible component can have a diameter of about 1 to 20 μm , a length of 50 to 600 μm and a conductivity of about 10^{-2} to 10^{-7} Ω/cm . In order to maintain the adhesive at a viscosity sufficient to be sprayed, the volumetric fraction of first and

metallic metals (e.g., iron, nickel, magnetic stainless steel, alloys thereof, etc.), non-metallic metals (e.g., aluminum, titanium, silver, gold, magnesium, nonmagnetic stainless steel, copper, chromium and alloys thereof, etc.), and silicon carbide.

Chemical dopants can also be incorporated into the molecular structure of the adhesive and can be either a strong dipole or electron acceptor, such as I, AsF₆, or ClO₄, or an electron donor, such as Li, Na, or K.

In operation, a substrate or workpiece is bonded to a similar or dissimilar material, e.g., wood to wood, wood to plastic, plastic to plastic, semi-conductor material to semi-conductor material, semi-conductor material to plastic, etc. by applying the adhesive of the present invention using commonly used and known techniques (e.g., spraying) to the substrate or other material or both; subjecting the adhesive to single frequency microwaves or preferably variable frequency microwaves using apparatus such as described in U.S. Patent No. 5,321,222 to Bible et al., the disclosure of which is incorporated herein by reference in its entirety; and thereby curing the adhesive to form the bond.

By selecting frequencies and powers that cure or soften a particular adhesive essentially without causing excessive heating of the substrates, deformation and other heat-related damage is avoided. The practical range of frequencies within the electromagnetic spectrum from which microwave frequencies may be chosen is about 0.90 GHz to 40 GHz. Every substrate or workpiece irradiated with microwave energy typically has at least one bandwidth, or window of frequencies within this overall range, that will cure or soften the adhesive without damaging the substrates. The term "window" as used herein, refers to a range of microwave frequencies bounded on one end by a specific frequency and bounded on the opposite end by a different specific frequency. Outside a particular window of damage-free frequencies, substrates may become deformed or otherwise damaged. A window may vary, depending on the component configuration, geometry, and composition of both substrates and adhesives. A workpiece may have a plurality of such windows. With the information set forth herein, a skilled practitioner will be able to select damage-free windows for a particular workpiece, whether empirically, through trial and error, or theoretically, using power reflection curves and the like.

Within a window of damage-free frequencies for a particular workpiece, it generally is preferred to select those frequencies that result in the shortest processing time. Typically, the time required to form the bond is set by the time required to cure a thermoset adhesive or to soften a thermoplastic adhesive. Preferably, a workpiece is processed with a subset of frequencies from the upper end of each window. More modes can be excited with higher frequencies than with lower frequencies. Therefore, better uniformity in processing typically is achieved. Additionally, at the higher frequency, more microwave energy is imparted to the workpiece, and energy absorption depth is more shallow. Greater microwave energy absorption and lesser microwave penetration depth result in shorter processing time. However, any subset of frequencies within a window of damage-free frequencies may be used.

Many workpieces irradiated with microwave energy have multiple windows of frequencies within which a thermoset adhesive will cure or a thermoplastic resin will soften without causing damage to the substrates. For example, a particular workpiece may be irradiated with microwave energy without damage at frequencies between 3.50 GHz and 6.0 GHz, and also may be irradiated without damage between 7.0 GHz and 10.0 GHz. The availability of additional windows provides additional flexibility for achieving rapid, yet damage-free bonding. Complex geometrical configurations and material combinations may shrink or close a window of processing frequencies otherwise available. The availability of alternative windows permits bonding of a workpiece using microwave irradiation without having to resort to other curing methods.

Preferably, the step of curing is performed by "sweeping" the workpiece with variable frequencies from within a particular window of damage-free frequencies. The term "sweeping" as used herein, refers to irradiating the substrate or workpiece,

i.e., the adhesive(s) and the substrates, with many of the frequencies within a particular window. Frequency sweeping results in uniformity of heating because many more complementary cavity modes can be excited. The uniformity in processing afforded by frequency sweeping provides flexibility in how groups of components to be bonded are oriented within the microwave furnace. Therefore, it is not necessary to maintain each workpiece in precisely the same orientation.

Sweeping may be accomplished by launching the different frequencies, either simultaneously or sequentially, within a window. For example, for a window of damage-free frequencies of from 2.60 GHz to 7.0 GHz, frequency sweeping involves continuously and/or selectively launching frequencies within this range in any desirable increments. Thus, moving from 2.6 to 3.3 GHz in increments of 0.0001 GHz would be acceptable. Indeed, virtually any incremental launching pattern may be used.

The rate at which the selected frequencies are launched is referred to as the sweeping rate. This rate may be any time value, including, but not limited to, milliseconds, seconds, and minutes. Preferably, the sweep rate is as rapid as practical for the particular substrate or workpiece being processed.

The following examples are provided for illustration purposes, and are not intended to be limiting as to the scope of the present invention.

20

Examples

Example 1

In order to demonstrate the correlation of fiber size, conductivity and distribution, five types of fiber were selected. The fibers are as follows:

Fiber Type	Electric Resistivity (Ω/cm)	Diameter (μm)	Length (μm)
Pyrograf III Carbon fiber available from Applied Science, Inc.	0.0015	.02	40-200
Carboflex Pitch-Based Carbon fibers available from Textron Systems	0.0060	12	200
Panex 33MF available from Zoltek Corporation	0.0014	7.4	150
Thornel® available from Amoco	0.0003	10	200
Chaff available from Tracor	10	18	200-350

5 A pigment, TiO_2 , was included. The particle size diameter was $<5\mu\text{m}$ and had a density of 4.17. The rate of heating of and microwave frequency(s) of a HB Fuller HL 6444 adhesive was then measured for the following combinations and the heating curve is shown in Figure 1.

Graph Line	Combination
A	0.1% Pyrograf III, 3% Panex 33MF, 8.5% TiO_2
B	0.1% Pyrograf III, 4% Carboflex, 8.5% TiO_2
C	0.1% Pyrograf III, 7% Chaff, 7.5% TiO_2
D	0.1% Pyrograf III, 6% Chaff, 8.5% TiO_2
E	0.1% Pyrograf III, 5% Chaff, 8.5% TiO_2

10 As the graph illustrates, small amounts of a second microwave susceptible component can be added so long as a good mix of conductivity is preselected.

Example 2

15 In order to demonstrate that advantages to the use of first and second microwave susceptible components, the following rates of heating of HB Fuller HL 6444 was measured and the heating curve shown in Figure 1.

Graph Line	Combination
F	5% Panex 33MF, 0.15% Pyrograf III
G	5% Panex 33MF
H	4% Panex 33MF, 0.15% Pyrograf III
I	4% Panex 33MF

As the graph illustrates, there is a significant increase in rate of heating when both first and second microwave susceptible components are used as compared to a single microwave susceptible component.

The present invention has been described in detail above. This invention may, however, be embodied in many different forms and should not be construed as limited to the embodiments set forth herein above; rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the invention to those skilled in the art.

THAT WHICH IS CLAIMED:

1. A microwave curable adhesive comprising a polymer composition and a mixture of first and second microwave susceptible components, each first and second microwave susceptible component within the mixture having a respective preselected size, preselected shape or preselected conductivity or combination thereof,
5 to provide a multi-modal distribution of first and second microwave susceptible components to increase microwave adsorption within said polymer composition.
2. The microwave curable adhesive according to Claim 1 wherein the polymer composition is a thermoset polymer.
3. The microwave curable adhesive according to Claim 2 wherein the thermoset polymer is selected from the group consisting of epoxies, phenol formaldehydes, urea-formaldehydes, melamine formaldehydes, polyesters, polyurethanes, cyanate esters, polybutadienes, alkyals, polyimides, amino resins and
5 silicons and blends and copolymers thereof.
4. The microwave curable adhesive according to Claim 1 wherein the polymer composition is a thermoplastic polymer.
5. The microwave curable adhesive according to Claim 4 wherein the thermoplastic polymer is selected from the group consisting of polyolefins, vinyl polymers, polycarbonates, polyamides, polystyrenes, polyetherimides, polyarylene sulfones, polyphenylene sulfides, polyphenylene oxides, polyethersulfones,
5 polyetherether ketones and blends and copolymers thereof.
6. The microwave curable adhesive according to Claim 1 wherein the first microwave susceptible component is a fiber having a diameter of about 0.01 to 0.1 μm and a length of about 10 to 300 μm and a conductivity of about 10^{-2} to 10^{-7} Ω/cm , and

-12-

second microwave susceptible component is a particle having a particle size, a diameter of about 1 to 40 μm and a conductivity of about 10^{-2} to 10^{-7} Ω/cm .

7. The microwave curable adhesive according to Claim 1 wherein said first conductive fibers have a first size, and wherein said second conductive fibers have a second size substantially larger than said first size.

8. A microwave curable adhesive comprising a polymer composition and a network of interconnected first and second conductive fibers dispersed within said polymer composition such that said adhesive has a volumetric fraction of first and second conductive fibers of between 0.01% and 2% and a weight fraction of first
5 second conductive fibers of between 1% and 20%.

9. The microwave curable adhesive according to Claim 8 wherein said first conductive fibers have a first size, and wherein said second conductive fibers have a second size substantially larger than said first size.

10. The microwave curable adhesive according to Claim 9 having a viscosity of less than 500 centipoise at a temperature of between room temperature and 250°C.

11. The microwave curable adhesive according to Claim 8 wherein the polymer composition is a thermoset polymer.

12. The microwave curable adhesive according to Claim 11 wherein the thermoset polymer is selected from the group consisting of epoxies, phenol formaldehydes, urea-formaldehydes, melamine formaldehydes, polyesters, polyurethanes, cyanate esters, polybutadienes, alkyals, polyimides, amino resins and
5 silicones and blends of copolymers thereof.

13. The microwave curable adhesive according to Claim 8 wherein the polymer composition is a thermoplastic polymer.

14. The microwave curable adhesive according to Claim 13 wherein the thermoplastic polymer is selected from the group consisting of polyolefins, vinyl polymers, polycarbonates, polyamides, polystyrenes, polyetherimides, polyarylene sulfones, polyphenylene sulfides, polyphenylene oxides, polyethersulfones, polyetherether ketones and blends and copolymers thereof.

15. The microwave curable adhesive according to Claim 9 wherein said first conductive fibers have a diameter of about 0.01 to 1 μm , a length of about 10 to 300 μm and a conductivity of about 10^{-2} to 10^{-7} Ω/cm , and wherein said second conductive fibers have a diameter of about 1 to 20 μm , a length of about 50 to 600 μm and a conductivity of about 10^{-2} to 10^{-7} Ω/cm .

16. A method of bonding a substrate to similar to dissimilar material comprising the steps of:

applying a microwave curable adhesive comprising a polymer composition and a mixture of first and second microwave susceptible components, each first and second microwave susceptible component within the mixture having a respective preselected size, preselected shape or preselected conductivity or combination thereof and subjecting the microwave curable adhesive to variable frequency microwaves to cure the microwave curable adhesive.

17. The method according to Claim 16 wherein the polymer composition is a thermoset polymer.

18. The method according to Claim 17 wherein the thermoset polymer is selected from the group consisting of epoxies, phenol formaldehydes, urea-formaldehydes, melamine formaldehydes, polyesters, polyurethanes, cyanate esters,

-14-

polybutadienes, alkyals, polyimides, amino resins and silicones and blends and copolymers thereof.

19. The method according to Claim 16 wherein the polymer composition is a thermoplastic polymer.

20. The method according to Claim 19 wherein the thermoplastic polymer is selected from the group consisting of polyolefins, vinyl polymers, polycarbonates, polyamides, polystyrenes, polyetherimides, polyarylene sulfones, polyphenylene sulfides, polyphenylene oxides, polyethersulfones, polyetherether ketones and blends and copolymers thereof.

5

21. The method according to Claim 16 wherein the first microwave susceptible component is a fiber having a diameter of about 0.01 to 0.1 μm and a length of about 10 to 300 μm and a conductivity of about 10^{-2} to 10^{-7} Ω/cm , and second microwave susceptible component is a particle having a particle size, a diameter of about 1 to 40 μm and a conductivity of about 10^{-2} to 10^{-7} Ω/cm .


5

22. The method according to Claim 16 wherein said first conductive fibers have a first size, and wherein said second conductive fibers have a second size substantially larger than said first size.

23. The method according to Claim 16 wherein the first and second microwave susceptible components are conductive fibers, and are a network of interconnected first and second conductive fibers dispersed within said polymer composition such that said adhesive has a volumetric fraction of first and second conductive fibers of between 0.01% and 2% and a weight fraction of first second conductive fibers of between 1% and 20%.


5

FIG. 1



2/2

FIG. 2



INTERNATIONAL SEARCH REPORT

International Application No.
PCT/US 98/22329

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C09J9/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C09D C09J C08J H01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 120 176 A (BHATIA SUSHIL K ET AL) 9 June 1992 see claims 20-23 ---	1, 4, 5, 16, 19, 20
X	EP 0 316 557 A (UTZ AG GEORG) 24 May 1989 cited in the application see claims 1, 19 see page 4, line 49 - line 54 see example 2 ---	1, 4, 5, 16, 19, 20
A	US 4 626 642 A (WANG CHEN-SHIH ET AL) 2 December 1986 cited in the application see claims --- -/--	1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

23 December 1998

Date of mailing of the international search report

07/01/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Niaounakis, M

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 98/22329

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 92 09503 A (MINNESOTA MINING & MFG) 11 June 1992 see claims 1,11-13 see page 14, line 18 - line 34 ---	1
A	FR 2 555 188 A (ELECTRICITE DE FRANCE) 24 May 1985 see claims 1,3,5 ---	1
A	EP 0 424 132 A (MINNESOTA MINING & MFG) 24 April 1991 see claims 1,2 ---	1
A	WO 93 10960 A (MINNESOTA MINING & MFG) 10 June 1993 see claim 1 see page 4, line 10 - page 5, line 2; figure 1 ---	1
A	DATABASE WPI Section Ch, Week 8921 Derwent Publications Ltd., London, GB; Class A21, AN 89-154529 XP002088802 & JP 01 095174 A (NIPPON OIL SEAL IND CO LTD), 13 April 1989 see abstract -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/22329

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5120176	A	09-06-1992	AU 2384392 A WO 9302867 A	02-03-1993 18-02-1993
EP 0316557	A	24-05-1989	DE 3802881 A JP 1165680 A US 4906497 A	24-05-1989 29-06-1989 06-03-1990
US 4626642	A	02-12-1986	NONE	
WO 9209503	A	11-06-1992	CA 2095118 A EP 0558655 A JP 6503536 T	30-05-1992 08-09-1993 21-04-1994
FR 2555188	A	24-05-1985	DE 3511654 A	02-10-1986
EP 0424132	A	24-04-1991	US 5189078 A AU 3028692 A AU 634281 B AU 6207390 A CA 2024923 A DE 69019457 D DE 69019457 T JP 3153790 A US 5238975 A	23-02-1993 18-03-1993 18-02-1993 26-04-1991 19-04-1991 22-06-1995 25-01-1996 01-07-1991 24-08-1993
WO 9310960	A	10-06-1993	US 5245151 A BR 9206805 A CA 2123689 A CN 1072802 A DE 69222181 D DE 69222181 T EP 0615487 A ES 2106203 T JP 7501760 T MX 9206848 A	14-09-1993 31-10-1995 10-06-1993 02-06-1993 16-10-1997 02-04-1998 21-09-1994 01-11-1997 23-02-1995 01-07-1993